

TITLE OF THE INVENTION

SEMICONDUCTOR DEVICE HAVING A WIRING LAYER OF DAMASCENE
STRUCTURE AND METHOD FOR MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application is based upon and claims the
benefit of priority from the prior Japanese Patent
Application No. 2000-185152, filed June 20, 2000, the
entire contents of which are incorporated herein by
reference.

10 BACKGROUND OF THE INVENTION

 The present invention relates to a semiconductor
device having a wiring layer of damascene structure and
a method for manufacturing the semiconductor device.
More specifically, the present invention relates to a
15 damascene technique that is very useful for
miniaturizing a semiconductor device and decreasing the
size of a chip.

 Miniaturization of semiconductor devices has
recently been advanced to make a wiring layer difficult
20 to form by conventional RIE (Reactive Ion Etching).
This difficulty is ascribed to difficulties in
improvement of yields and flattening when a conductive
film is microfabricated by the RIE. As a technique of
resolving this problem, a wiring layer of damascene
25 structure (referred to as a damascene wiring layer) has
been known conventionally.

 FIGS. 9A to 9C schematically show a process of

2000-185152-0001

THE UNIVERSITY OF CHICAGO

THE UNIVERSITY OF CHICAGO

[illegible][illegible]

THE UNIVERSITY OF CHICAGO

tungsten (W) and serves as a glue layer or a barrier layer in reflowing of aluminum (Al).

The resistivity of the barrier metal film 105 is generally higher than that of the conductive film 107.

5 Therefore, the prior art semiconductor device described above had a problem that the resistance of the damascene wiring layer was higher than a wiring layer formed by the RIE method (referred to as an RIE wiring layer hereinafter).

10 FIGS. 10A and 10B illustrate a damascene wiring layer and an RIE wiring layer having the same line width L for purposes of comparison.

In the damascene wiring layer 109 shown in FIG. 10A, the barrier metal film 105 is formed on
15 each sidewall of the conductive film 107. Thus, the width L' of the conductive film 107 is smaller than the line width L of the damascene wiring layer 109 by two times (2b) the thickness of the barrier metal film 105 ($L' = L - 2b < L$). In the RIE wiring layer 201
20 shown in FIG. 10B, the width L' of the conductive film 107 is equal to the line width L of the RIE wiring layer 201 ($L' = L$). In other words, the cross-sectional area (volume) of the conductive film 107 in the damascene wiring layer 109 is relatively smaller
25 than that in the RIE wiring layer 201.

The thickness (b) of the barrier metal film 105 is determined appropriately to serve as a glue layer for

09883210-0619001

forming the conductive film 107, to secure adhesion enough to form the film 107, or to obtain good characteristics of contact with the interlayer insulation film 101. In short, the barrier metal film 105 having a given thickness or more is indispensable for forming the damascene wiring layer 109.

If the damascene technique is applied to the formation of wiring, the volume of the barrier metal film in the wiring increases relatively as a semiconductor device decreases in size. As a result, the cross-sectional area of the conductive film decreases and thus the resistance of the wiring increases, or a so-called thin-wire effect is problematic.

The above barrier metal film has the problems that it hardly contributes to a reduction in wiring resistance and narrows a distance between adjacent wiring layers and increases the capacitance between them.

The prior art damascene wiring layer has the problems that the wiring resistance increases and the wiring-to-wiring capacitance increases though the conductive film is improved in yield and easily flattened and the semiconductor device can sufficiently be miniaturized.

BRIEF SUMMARY OF THE INVENTION

An object of the present invention is to provide

0983210-061904

5 a semiconductor device capable of preventing wiring resistance from increasing and preventing wiring-to-wiring capacitance from increasing and easily improving in performance, and a method for manufacturing the semiconductor device.

10 In order to attain the above object, a semiconductor device according to a first aspect of the present invention comprises a first insulation film provided above a semiconductor substrate, a conductive film selectively provided at least on a bottom of a groove section formed in the first insulation film and a wiring layer formed on the conductive film so as to have a space region between the wiring layer and at least one sidewall of the groove section.

15 A semiconductor device according to a second aspect of the present invention comprises a first insulation film provided above a semiconductor substrate, a wiring layer buried in the first insulation film, a conductive film provided at least on a bottom of the wiring layer, and a fourth insulation film formed on at least one side of the wiring layer, the fourth insulation film being different from the first insulation film.

20 A semiconductor device according to a third aspect of the present invention comprises an insulation film provided above a semiconductor substrate, a wiring layer buried in the insulation film, a first conductive

0955210-061004

A semiconductor device according to a fourth aspect of the present invention comprises a first insulation film provided above a semiconductor substrate, at least two wiring layers buried in the first insulation film, a first conductive film provided on a bottom of each of the wiring layers, a fifth insulation film formed on at least one side of each of the wiring layers, and a contact plug provided between the two wiring layers with the fifth insulation film interposed therebetween.

A method of manufacturing a semiconductor device according to a sixth aspect of the present invention,

5 a first conductive film in the groove section along
the third insulation film, forming a buried wiring
layer in the groove section with the first conductive
film interposed therebetween, and selectively removing
the third insulation film from at least one sidewall
10 portion of the groove section to form a space region
between the sidewall portion and one side of the wiring
layer.

A method of manufacturing a semiconductor device according to a seventh aspect of the present invention, comprises the steps of forming at least two groove sections in a first insulation film provided above a semiconductor substrate, forming a first conductive film on the first insulation film along each of the two groove sections, forming a buried wiring layer in each of the two groove section with the first conductive film interposed therebetween, selectively removing the first conductive film from at least one sidewall portion of each of the two groove section, and forming a contact plug between the two groove sections with a fifth insulation film interposed therebetween.

According to the semiconductor device and the method for manufacturing the same described above,

5 Additional objects and advantages of the invention
will be set forth in the description which follows, and
in part will be obvious from the description, or may
be learned by practice of the invention. The objects
and advantages of the invention may be realized and
10 obtained by means of the instrumentalities and combina-
tions particularly pointed out hereinafter.

The accompanying drawings, which are incorporated in and constitute a part of the specification, illustrate presently preferred embodiments of the invention, and together with the general description given above and the detailed description of the preferred embodiments given below, serve to explain the principles of the invention.

FIGS. 2A to 2F are cross-sectional views showing
25 a process of forming the damascene wiring layer of the
semiconductor device according to the first embodiment
of the present invention;

5

10

15

20

25

example of the semiconductor device according to

the sixth embodiment of the present invention;

FIGS. 9A to 9C are cross-sectional views showing a process of manufacturing a semiconductor device having a damascene wiring layer (a method of forming a damascene wiring layer) in order to describe a prior art technique and its problems; and

FIGS. 10A and 10B are cross-sectional views showing a damascene wiring layer and an RIE wiring layer having the same line width in the prior art technique for purposes of comparison.

DETAILED DESCRIPTION OF THE INVENTION

Embodiments of the present invention will now be described with reference to the accompanying drawings.
(First Embodiment)

15 FIG. 1 schematically shows a cross section of
a semiconductor device having a damascene wiring layer
according to a first embodiment of the present
invention.

In FIG. 1, a silicon oxide film (insulation
film/first insulation film) 12 is provided directly or
indirectly on a semiconductor substrate 11. A wiring
pattern groove (groove section) 13 is formed in
a surface portion of the silicon oxide film 12.
A barrier metal film (conductive film/first conductive
film) 14 is selectively formed only on the bottom of
the groove 13. A wiring layer 16, which is constituted
of a conductive film, is provided on the barrier metal

5

10

15

20

25

Then, as shown in FIG. 2B, a TiN film 14' serving as a barrier metal film 14 is deposited on the entire surface of the resultant structure to a given thickness. The TiN film 14' is formed by CVD (Chemical

Vapor Deposition) using an organic raw-material gas.

Referring to FIG. 2C, only the quality of the TiN film 14a' exposed to at least the bottom of the groove 13 is changed by anisotropic plasma processing.

5 The just-deposited TiN film contains a large number of organic impurities such as carbon. The TiN film is low in density and very unstable. Therefore, the TiN film should be changed to a dense one by scattering the impurities by plasma processing.

10 Since the plasma processing is anisotropic, the TiN film 14b formed on the sidewalls of the groove 13 is hardly exposed to plasma. The TiN film 14b' remains unstable to cause a difference in quality between the TiN film 14b' and the TiN film 14a' formed on the
15 bottom of the wiring pattern groove 13.

As FIG. 2D illustrates, a conductive film (e.g., W) 16', which is to serve as a wiring layer 16, is deposited on the entire surface of the resultant structure by CVD to completely fill the groove 13.

20 As FIG. 2E illustrates, a wiring layer 16 is formed by flattening the surface of the resultant structure by CMP. In this case, the conductive film 16' and TiN film 14' are selectively removed until the top surface of the silicon oxide film 12 is exposed
25 and, in other words, they are selectively removed from the silicon oxide film 12 but not from inside the groove 13.

00883210-061904

5

15

20

25

the plasma SiO₂ film 17 the coverage characteristics of which are poor, is used effectively as the hollow section 15. The present invention is not limited to this feature. For example, the etching region 15a can
5 be filled with an insulation film (fourth insulation film) 21, as illustrated in FIGS. 3A to 3C.

After the step shown in FIG. 3A which is the same as that shown in FIG. 2F of the first embodiment, an insulation film 21 whose burying characteristics
10 are improved is deposited on the entire surface of the resultant structure in place of the plasma SiO₂ film 17, as illustrated in FIG. 3B. By flattening the insulation film 21 by CMP as shown in FIG. 3C, it is left only in the etching region 15a. For example,
15 a TEOS (Tetraethyl Orthosilicate) film formed by plasma CVD or an SOG (Spin On Glass) film formed by coating is used as the insulation film 21.

In the second embodiment, when a damascene wiring layer is formed, the side portions of a wiring layer 16
20 can be used as insulation regions by substituting the insulation film 21 for regions (sidewalls of wiring pattern groove 13) in which the barrier metal film 14 is originally provided. If, therefore, the wiring pattern groove 13 is widened in advance by the
25 thickness of the barrier metal film 14, an increase in wiring resistance due to microfabrication can be suppressed effectively.

TOP SECRET

(Third Embodiment)

FIGS. 4A to 4C schematically show a process of manufacturing a semiconductor device having a damascene wiring layer (a method of forming a damascene wiring layer) according to a third embodiment of the present invention. In the third embodiment, the process up to the step of selectively removing the TiN film 14b' from the sidewalls of the wiring pattern groove 13 is the same as that shown in FIGS. 2A to 2F of the first embodiment. The steps subsequent thereto will now be described below.

The TiN film 14b' is selectively removed from the sidewalls of the groove 13 by SC-2 processing to form a barrier metal film 14 (see FIG. 4A). Then, a W film (second conductive film) 31 is deposited on the entire surface of the resultant structure by sputtering or CVD, as shown in FIG. 4B.

As FIG. 4C illustrates, the resultant structure is flattened by CMP and the W film 31 is removed until the top surface of a silicon oxide film 12 is exposed. Thus, an etching region 15a between each side of the wiring layer 16 and each sidewall of the groove 13 is completely filled with the W film 31.

In the third embodiment, too, the side portions of the wiring layer 16 can be used as wiring regions by substituting the W film 31 for regions (sidewalls of the groove 13) in which the barrier metal film 14 is

originally provided. The line width of a damascene wiring layer can thus be increased by the thickness of the barrier metal film 14. In other words, the region corresponding to the thickness of the barrier metal film 14 can be used as a wiring layer without waste. A semiconductor device with the above damascene wiring layer can be microfabricated without increasing the resistance of wiring.

Not only the W film but also any other conductive film can be used as the second conductive film that is buried into the etching region 15a.

(Fourth Embodiment)

In the first to third embodiments, a spacer (third insulation film) can be provided on each sidewall of the wiring pattern groove 13.

FIGS. 5A to 5G schematically show a process of manufacturing a semiconductor device having a damascene wiring layer (a method of forming a damascene wiring layer) according to a fourth embodiment of the present invention. The fourth embodiment will now be described in brief, taking the first embodiment in which the hollow section 15 is provided between each sidewall of the wiring pattern groove 13 and each side of the wiring layer 16 as an example.

A silicon oxide film 12 is formed directly or indirectly on a semiconductor substrate 11. A wiring pattern groove 13 is formed in a surface portion of

the silicon oxide film 12 by known lithography and RIE. After that, a SiN (silicon nitride) film serving as a third insulation film is deposited on the surface of the silicon oxide film 12 by CVD. Then, the SiN film
5 is selectively removed by anisotropic etching and left only on each sidewall of the groove 13, thereby forming a spacer 41 (see FIG. 5A).

If the same steps as those of FIGS. 2B et seq. are executed after the above step, a semiconductor device
10 having a damascene wiring layer can be obtained in which the spacer 41 is provided on each sidewall of the groove 13 and the hollow section 15 is formed between the spacer 41 and each side of the wiring layer 16.

The structure of the fourth embodiment can produce
15 an advantage as well as that of the first embodiment. Not only wiring-to-wiring capacitance can effectively be reduced maintaining a high yield, but also wiring-to-wiring insulating characteristics can be improved further. The semiconductor device can thus be
20 microfabricated more greatly.

In the fourth embodiment, too, an insulation film 21, a W film or the like can easily be buried into the etching region 15a in place of the hollow section 15, as in the second and third embodiments described above.
25 (Fifth Embodiment)

FIGS. 6A to 6E schematically show a process of manufacturing a semiconductor device having a damascene

wiring layer (a method of forming a damascene wiring layer) according to a fifth embodiment of the present invention. The fifth embodiment is directed to a case where a hollow section 15 is formed by removing the
5 spacer 41, which is formed on each sidewall of the wiring pattern groove 13 in the fourth embodiment.

Referring first to FIG. 6A, a silicon oxide film 12 is formed directly or indirectly on a semiconductor substrate 11 and a wiring pattern groove 13 is formed
10 in a surface portion of the silicon oxide film 12 by known lithography and RIE.

After that, as shown in FIG. 6B, a SiN film serving as a third insulation film is deposited on the surface of the silicon oxide film 12 by CVD. The SiN
15 film is selectively removed by anisotropic etching and left only on each sidewall of the groove 13, resulting in spacers 41.

A TiN film serving as a barrier metal film 14 is deposited on the entire surface of the resultant structure and a W film serving as a wiring layer 16 is
20 deposited thereon. As FIG. 6C illustrates, the resultant structure is flattened by CMP until the top surface of the silicon oxide film 12 is exposed, resulting in the barrier metal film 14 and the wiring
25 layer 16.

Wet etching in phosphoric acid allows the spacers 41 to be selectively removed from the sidewalls of

the groove 13, as shown in FIG. 6D.

Referring to FIG. 6E, a plasma SiO₂ film 17 is deposited on the entire surface of the resultant structure by plasma CVD. The film 17 inhibits the etching region 15a excluding the spacers 41 from being filled completely. Consequently, a semiconductor device having a damascene wiring layer can be manufactured in which a hollow section 15 is provided along each sidewall of the groove 13.

The etching region 15a is therefore prevented from being filled completely using a film of poor coverage characteristics such as plasma SiO₂ on purpose. As in the first embodiment, the hollow section 15 can easily be formed along each sidewall of the wiring pattern groove 13 excluding the spacers 41. The section 15 allows the wiring-to-wiring capacitance to be reduced effectively.

According to the fifth embodiment, the hollow section 15 can be formed along each side of the wiring layer 16 with good controllability even when the barrier metal film 14 is difficult to selectively remove from the wiring layer 16 or even though no anisotropic plasma processing is executed.

(Sixth Embodiment)

FIGS. 7A to 7E schematically show a process of manufacturing a semiconductor device having a damascene wiring layer (a method of forming a damascene wiring

5 selectively etched to form a contact hole 54 reaching the semiconductor substrate 11. The contact hole 54 is formed in self-alignment with the silicon nitride film 52 (see FIG. 7E).

10 film serving as a barrier metal film (third conductive
film) 55 and a conductive film (e.g., tungsten) serving
as a storage node contact (fourth conductive film) 56
are deposited on the entire surface of the resultant
structure by CVD to fill the contact hole 54
15 completely. By flattening the structure by CMP until
the top surface of the silicon oxide film 12 is
exposed, a contact plug is formed of the barrier metal
film 55 and the storage node contact 56 (see FIG. 7F).

After that, a capacitor and a plate electrode are
20 formed in the same manner as those of the normal DRAM
cell.

25 capacitor. No margin for alignment is required for forming the contact hole 54. Therefore, a distance between bit lines 51 can sufficiently be reduced and

In particular, sidewalls 53 for insulating the bit lines 51 and the storage contact 56 from each other are formed at the same time when the silicon nitride film 52 is buried into the step region 15b. The number of manufacturing steps can thus be reduced. Moreover, the regions (side portions of the bit lines 51) that correspond to those occupied by the barrier metal film can effectively be used as the sidewalls 53. Consequently, a so-called thinning effect of increasing the resistance of the bit lines 51 can easily be suppressed.

20 If the present invention is applied to the DRAM cell using a stacked capacitor, a spacer (fifth insulation film) 41' can be provided at least between the wiring pattern groove 13 and the contact hole 54, as illustrated in FIG. 8. In this case, a hollow
25 section 15 can be formed between the bit line 51 and the spacer 41' as in the fourth embodiment (see FIGS. 5A to 5G). The capacitance between the bit line

51 and the storage node contact 56 can effectively be reduced.

In the foregoing embodiments of the present invention, a hollow section is provided along each sidewall of the wiring pattern groove. The present invention is not limited to this structure. The hollow section can be provided only on the sidewall adjacent to at least another damascene wiring layer.

5

10